

1-AO History

Brillouin predicted the light diffraction by an acoustic wave, being propagated in a medium of interaction, in 1922.

In 1932, Debye and Sears, Lucas and Biquard carried out the first experimentations to check the phenomena.

The particular case of diffraction on the first order, under a certain angle of incidence, (also predicted by Brillouin), has been observed by Rytow in 1935.

Raman and Nath (1937) have designed a general ideal model of interaction taking into account several orders. This model was developed by Phariseau (1956) for diffraction including only one diffraction order.

At this date, the acousto-optic interaction was only a pleasant laboratory experimentation. The only application was the measurement of constants and acoustic coefficients.

The laser invention has led the development of acousto-optics and its applications, mainly for deflection, modulation and signal processing. Technical progresses in both crystal growth and high frequency piezoelectric transducers have brought valuable benefits to acousto-optic components improvements.

2-Glossary

Bragg cell: A device using a bulk acousto-optic interaction (eg. deflectors, modulators, etc...).

“Zero” order, “1st” order: The zero order is the beam directly transmitted through the cell. The first order is the diffracted beam generated when the laser beam interacts with the acoustic wave.

Bragg angle (QB): The particular angle of incidence (between the incident beam and the acoustic wave) which gives efficient diffraction into a single diffracted order. This angle will depend on the wavelength and the RF frequency.

Separation angle (Q): The angle between the zero order and the first order.

RF Bandwidth (DF): For a given orientation and optical wavelength there is a particular RF frequency which matches the Bragg criteria. However, there will be a range of frequencies for which the situation is still close enough to optimum for diffraction still to be efficient. This RF bandwidth determines, for instance, the scan angle of a deflector or the tuning range of an AOTF.

Maximum deflection angle (DQ): The angle through which the first order beam will scan when the RF frequency is varied across the full RF bandwidth.

Rise time (TR): Proportional to the time the acoustic wave takes to cross the laser beam and, therefore, the time it takes the beam to respond to a change in the RF signal. The rise time can be reduced by reducing the beam’s width.

2-Glossary

Modulation bandwidth (DF_{mod}): The maximum frequency at which the light beam can be amplitude modulated. It is related to the rise time - and can be increased by reducing the diameter of the laser beam.

Efficiency (h): The fraction of the zero order beam which can be diffracted into the “1st” order beam.

Extinction ratio (ER): The ratio between maximum and minimum light intensity in the “1st” order beam, when the acoustic wave is “on” and “off” respectively.

Frequency shift (F): The difference in frequency between the diffracted and incident light beams. This shift is equal to the acoustic frequency and can be a shift up or down depending on orientation.

Resolution (N): The number of resolvable points, which a deflector can generate - corresponding to the maximum number of separate positions of the diffracted light beam - as defined by the Rayleigh criterion.

RF Power (PRF): The electrical power delivered by the driver.

Acoustic power (P_a): The acoustic power generated in the crystal by the piezoelectric transducer. This will be lower than the RF power as the electro-mechanical conversion ratio is lower than 1.

3-Physical Principles

An RF signal applied to a piezo-electric transducer, bonded to a suitable crystal, will generate an acoustic wave. This acts like a “phase grating”, traveling through the crystal at the acoustic velocity of the material and with an acoustic wavelength dependent on the frequency of the RF signal. Any incident laser beam will be diffracted by this grating, generally giving a number of diffracted beams.

3-1 Interaction conditions

A parameter called the “quality factor, Q ”, determines the interaction regime. Q is given by:

$$Q = \frac{2\pi\lambda_0 L}{n\Lambda^2}$$

where λ_0 is the wavelength of the laser beam, n is the refractive index of the crystal, L is the distance the laser beam travels through the acoustic wave and Λ is the acoustic wavelength.



$Q \ll 1$: This is the Raman-Nath regime. The laser beam is incident roughly normal to the acoustic beam and there are several diffraction orders (...-2 -1 0 1 2 3...) with intensities given by Bessel functions.

$Q \gg 1$: This is the Bragg regime. At one particular incidence angle Θ , only one diffraction order is produced - the others are annihilated by destructive interference.

In the intermediate situation, an analytical treatment isn't possible and a numerical analysis would need to be performed by computer.

Most acousto-optic devices operate in the Bragg regime, the common exception being acousto-optic mode lockers and Q-switches.

3-Physical Principles

Diffraction Ways	Diagrams of Principle
Raman-Nath diffraction	 <p>The diagram illustrates Raman-Nath diffraction. At the top, an RF driver (represented by a sine wave symbol) is connected to a Pizeo-electric transducer. This transducer is mounted on a crystal of acousto-optic interaction. An incident light beam enters from the left. The interaction with the acoustic wave in the crystal results in several diffraction orders, labeled as -2, -1, 0, +1, and +2, exiting to the right.</p>
Bragg diffraction	 <p>The diagram illustrates Bragg diffraction. Similar to the Raman-Nath setup, it features an RF driver, a Pizeo-electric transducer, and a crystal of acousto-optic interaction. An incident light beam enters from the left. The acoustic wave in the crystal is oriented such that the light is diffracted into two main orders: the 1st order and the 0 order. The angle of incidence is labeled as θ, and the angle of the 1st order is labeled as 2θ.</p>


Acousto-optic Q-Switches

Acousto-optic Q-Switches

When placed inside a laser cavity, an acousto-optic Q-switch (AOQS) can be used to control the amount of light circulating within the resonator via the acousto-optic effect. When turned on, an AOQS diffracts light out of the optical beam path within the cavity, thus increasing losses and reducing the Q-factor. While loss in the cavity is high and pumping continues, lasing cannot occur, but a population inversion can build up within the gain medium. Once the gain is saturated, the RF power to the acousto-optic Q-switch is turned off, reducing loss within the cavity very quickly. This increases the Q-factor and allows rapid amplification to create a very high intensity, short pulse.

A high quality acousto-optic Q-switch has several important characteristics:

- Very low loss in the “off” state to maximize output intensity
- Ability to withstand very high peak laser power
- Excellent transducer reliability to allow long-term use without maintenance



Products

OPERATING FREQUENCY	PRODUCT CODE	WAVE-LENGTH	ACTIVE APERTURE	OPTICAL MATERIAL	COOLING	PAGE
27.12MHz	CAQS-027-6-1064-N-01	1064nm	6mm	Fused Silica	Water-cooled	
40.68MHz	CAQS-041-1-1064-A-02	1064nm	1mm	Crystalline quartz	Conduction-Cooled	
	CAQS-041-1.5-1064-A-02	1064nm	1.5mm	Crystalline quartz	Conduction-Cooled	
	CAQS-041-1.8-1064-A-02	1064nm	1.8 mm	Crystalline quartz	Conduction-Cooled	
	CAQS-041-2-1064-A-02	1064nm	2mm	Crystalline quartz	Conduction-Cooled	
80MHz	CAQS-080-1-1064-A-02	1064 nm	1mm	Crystalline Quartz	Conduction-Cooled	
	CAQS-080-1.5-1064-A-02	1064 nm	1.5mm	Crystalline Quartz	Conduction-Cooled	

CAQS-027-6-1064-N-01

Features

- ☐ 1064 nm
- ☐ Water cooling
- ☐ High damage threshold
- ☐ High efficiency
- ☐ Stable performance

Applications

- ☐ Material processing
- ☐ Medical
- ☐ Scientific




Specifications

Material	Fused Silica
Wavelength	1064 nm
Transmission (Single pass)	≥99.6%
Damage threshold	> 1GW/cm ²
Polarization	random
Aperture	6 mm
RF Frequency	27 MHz
RF power rating (Maximum)	100 W
RF connector	BNC
Thermal Security connector	SMB
Operating mode	Raman Nath
Diffraction efficiency	Nom > 60%
Input impedance	50 Ω
VSWR	< 1.2:1
Water flow rate	> 190 cc/minute
Operating temperature	10°C ~ 40°C
Storage temperature	0°C ~ 50°C

CAQS-027-6-1064-N-01

Dimensions



Order Information

CAQS — 027 — 6 — 1064 — N — 01

Frequency

027 — 27MHz

Aperture

6 — 6mm

Wavelength

1064 — 1064nm

Connector

B — BNC

Material

01 — Fused Silica


CAQS-041-X-1064-A-02

Features

- u Compact package
- u Conduction-cooled
- u High damage threshold
- u High efficiency
- u Stable performance

Applications

- u Material processing
- u Medical
- u Biomedical
- u Scientific




Specifications

Material	Crystal Quartz
Wavelength	1064 nm
Transmission (Single pass)	≥99.6%
Damage threshold	>1GW/cm ²
AR coating reflection	<0.2% per surface
Polarization	Linear, vertical to base
Aperture	1,1.5,1.8,2 mm
Acoustic mode	Compressional
RF Frequency	40.68 MHz
RF power rating (Maximum)	20 W
RF connector	SMA
Rise time (10~90%)	113 ns/mm
Loss Modulator	≥85%
VSWR	<1.2:1
Cooling	Conduction-cooled
Storage temperature	-20°C~70°C

CAQS-041-X-1064-A-02

Dimensions



Order Information

CAQS — 041 — X — 1064 — A — 02

Frequency

041 — 40.68MHz

Aperture

X(1,1.5,1.8,2) — 1,1.5,1.8,2mm

Wavelength

1064 — 1064nm

Connector

A — SMA

Material

02 — Crystal Quartz


CAQS-080-X-1064-A-02

Features

- u Compact package
- u Conduction-cooled
- u High damage threshold
- u High efficiency

Applications

- u Material processing
- u Medical
- u Scientific




Specifications

Material	Crystal Quartz
Wavelength	1064 nm
Transmission (Single pass)	≥99.6%
Damage threshold	>1GW/cm ²
AR coating reflection	<0.2% per surface
Polarization	Linear, vertical to base
Aperture	1,1.5 mm
Acoustic mode	Compressional
RF Frequency	80 MHz
RF power rating (Maximum)	15 W
RF connector	SMA
Rise time (10~90%)	113 ns/mm
Loss Modulator	≥85%
VSWR	<1.2:1
Cooling	Conduction-cooled
Storage temperature	-20°C~70°C

CAQS-080-X-1064-A-02

Dimensions



Order Information

CAQS — 080 — X — 1064 — A — 02

Frequency

080 — 80MHz

Aperture

X(1,1.5) — 1,1.5mm

Wavelength

1064 — 1064nm

Connector

A — SMA

Material

02 — Crystal Quartz

AOM-100-0.5-1064-C-03

Features

- u Compact package
- u Condition through baseplate
- u High damage threshold
- u High efficiency
- u Stable performance

Applications

- u Fiber laser
- u Optical sensing
- u Medical
- u Scientific




Specifications

Material	TeO ₂
Wavelength	1064 nm
Transmission (Single pass)	≥97%
Damage threshold	> 1GW/cm ²
Diffraction efficiency	Nom > 80%
Polarization	Random
Aperture	0.5 mm
Operating mode	Bragg
RF Frequency	100 MHz
RF power rating (Maximum)	< 2.5 W
RF connector	SMA
Rise time	< 120 ns
Input impedance	≥85%
VSWR	50 Ω
Operating temperature	10°C~40°C
Storage temperature	0°C~50°C

CAOM-100-0.5-1064-C-03

Dimensions



Order Information

CAOM — 100 — 0.5 — 1064 — C — 03

Frequency

100 — 100MHz

Aperture

0.5 — 0.5mm

Wavelength

1064 — 1064nm

Connector

C — SMC

Material

03 — TeO₂