


## Nd:KGW – Nd-DOPED POTASSIUM GADOLINIUM TUNGSTATE



Nd:KGW crystals are low lasing threshold, highly efficient laser material exceptionally suitable for laser rangefinding applications. The efficiency of Nd:KGW lasers is 3–5 times higher than the one of Nd:YAG lasers. Nd:KGW laser medium is one of the best choices ensuring effective laser generation at low pump energies (0.5 – 1 J). These crystals supplied by EKSMA OPTICS feature high optical quality and great value of bulk resistans for laser radiation.

### STANDARD SPECIFICATIONS

Orientation	[010] ± 30 min
Dopant concentration	2 – 10 at %
Diameter tolerance	+0.0 / -0.1 mm
Length tolerance	+1.0 / -0.0 mm
Chamfer	45(±10) deg × 0.2(±0.1) mm
Flatness	λ/10 @ 633 nm
Parallelism	better than 30 arcsec
Perpendicularity	better than 15 arcmin
Surface Quality	10 – 5 scratch & dig (MIL-PRF-13830B)
Absorption losses	< 0.005 cm <sup>-1</sup>

### PHYSICAL AND LASER PROPERTIES

Chemical formula	KGd(WO <sub>4</sub> ):Nd
Lattice constants	a = 8.095 Å, b = 10 Å, c = 7.588 Å
Optical orientation	n <sub>g</sub> = b, n <sub>p</sub> c = 20 deg
Angle between optical axis	86.5 angular grad
Density	7.27 g/cm <sup>3</sup>
Mohs hardness	5
Thermal conductivity	2.8 W/(mxgrad) [100] 2.2 W/(mxgrad) [010] 3.5 W/(mxgrad) [001]
Thermal expansion	4x10 <sup>-6</sup> grad <sup>-1</sup> [100] 3.6x10 <sup>-6</sup> grad <sup>-1</sup> [010] 8.5x10 <sup>-6</sup> grad <sup>-1</sup> [001]
Phase transition	1005 °C
Melting point	1075 °C
Transmission range	0.35–5.5 μm
Refractive index	n <sub>g</sub> = 2.033 @ 1.067 μm n <sub>p</sub> = 1.937 @ 1.067 μm n <sub>m</sub> = 1.986 @ 1.067 μm
Transition	<sup>4</sup> F <sub>3/2</sub> → <sup>4</sup> I <sub>11/2</sub>
Laser wavelength	1.0672 μm
Fluorescence lifetime	120 μs
Fluorescent width	24 cm <sup>-1</sup>
Emission cross-section	4.3x10 <sup>-19</sup> cm <sup>2</sup>
Emission temperature drift	8.5x10 <sup>-4</sup> nm, K <sup>-1</sup>