

Yb:YAG Yb-doped YAG



DESCRIPTION

Yb: YAG is a laser crystal which is doped with trivalent ytterbium ions in yttrium aluminum garnet crystal and can emit 1030 nm near-infrared laser. Yb: YAG crystal has characters of high quantum efficiency, no excited state absorption and up-conversion, high concentration tolerance, long fluorescence lifetime, wide absorption band and broad emission range and robust optical, mechanical and thermal properties etc., which makes it have great potential application in high efficiency, high power diode-pumped solid-state lasers.

APPLICATIONS

- 1030nm laser
- Diode pumping
- Human friendly in dental treatment field
- Yb: YAG amplifier module for optical fiber amplifier
- Material micromachining
- Holography, interference, optical storage and other fields
- YAG laser marker
- Laser cutting and welding
- Multiphoton microscopy
- Ultrashort pulse research
- LIDAR and optical refrigeration

FEATURES

- Good optical quality
- Wide absorption bands
- Low quantum defect
- High slope efficiency
- Low working temperature
- Linearly polarized emission and single-mode
- Simple energy level structure



Yb:YAG Yb-doped YAG

PARAMETERS


MATERIAL AND SPECIFICATIONS

| Property | Value |
|-----------------------------------|--|
| Yb Concentration Tolerance (atm%) | 0.5, 1, 2, 3, 5, 7.5 , 10, 15, 20, 25% |
| Orientation | [001] \ [110] \ [111] <±0.5° |
| Parallelism | 10" |
| Perpendicularity | 5' |
| Surface Quality | 10-5 |
| Wavefront Distortion | λ/4@632nm |
| Surface Flatness | λ/8@632nm |
| Clear Aperture | >95% |
| Chamfer | <0.1×45° |
| Thickness/Diameter Tolerance | ±0.05 mm |
| Maximum Dimensions | dia 50×100 mm |
| Coatings | AR/AR@940+1030; HR@940+AR1030 |

OPTICAL AND SPECTRAL PROPERTIES

| Property | Value |
|-----------------------------|--------------------------------------|
| Laser Transition | $^2F_{5/2} \rightarrow ^2F_{7/2}$ |
| Laser Wavelength | 1030 nm |
| Photon Energy | $1.93 \times 10^{-19} J (@ 1030 nm)$ |
| Pump Absorption Band Width | 8 nm |
| Loss Coefficient | 0.003 cm ⁻¹ |
| Diode Pump Band | 940 nm or 970 nm |
| Emission Cross Section | $2.0 \times 10^{-20} \text{ cm}^2$ |
| Fluorescence Lifetime | 1.2 ms |
| Emission Linewidth | 9 nm |
| Refractive Index @ 1.030 μm | 1.82 |
| Thermal Optical Coefficient | $9 \times 10^{-6}/^\circ C$ |

SPECTRA



PHYSICAL AND CHEMICAL PROPERTIES

| Property | Value |
|---|--|
| Crystal Structure | cubic – Ia3d |
| Lattice Constants | 12.01 Å |
| Density | $4.56 \pm 0.04 \text{ g/cm}^3$ |
| Melting Point | 1970 °C |
| Thermal Conductivity /($\text{W}\cdot\text{m}^{-1}\cdot\text{K}^{-1}$ @25°C) | λ/4@632nm |
| Specific Heat/ ($\text{J}\cdot\text{g}^{-1}\cdot\text{K}^{-1}$) | 0.59 |
| Thermal Optical Coefficient(d_n/dT) | $7.3 \times 10^{-6}/^\circ C$ |
| Thermal Expansion / ($10^{-6}\cdot\text{K}^{-1}$ @25°C) | 8.2 [100] 7.7 [110] 7.8 [111] |
| Hardness (Mohs) | 8.5 |
| Young's Modulus /GPa | 317 |
| Shear Modulus /Gpa | 54.66 |
| Extinction Ratio | 25 dB |
| Tensile Strength/Gpa | 0.13-0.26 |
| Solubility | Water: Insoluble; Common Acides: Slightly |
| Poisson Ratio | 0.25 |

